

Soil FACTSHEET



BRITISH
COLUMBIA

Ministry of Agriculture and Food

Order No. 637.200-2

Agdex: 530

January 1985

Evaluation of Agricultural Limestone

The efficiency of agricultural limestone for neutralizing soil acidity is influenced by four principal factors: degree of fineness, neutralizing capacity, solubility and magnesium content.

1. Degree of Fineness

The relationship between increasing limestone fineness and reactivity is caused by having a larger surface area exposed to chemical reaction. The surface area of liming material increases proportionately with decreasing particle size, for example, the exposed area of a cube of 1 cm is 6 cm²: decreasing the particle size to 2 mm (10 mesh), or 0.05 mm (300 mesh) increases the exposed area to 30 and 1200 cm², respectively. A practical way of adjusting for limestone reactivity due to differential particle sizes is the method developed in Ohio: This method assigns different liming efficiencies to various particle sizes determined by sieve analysis.

SIEVE	EFFICIENCY RATING (E.R.)
Material passing through a 60 mesh sieve	100%
Material passing through a 20, but not a 60 mesh sieve	60%
Material passing through an 8, but not a 20 mesh sieve	20%
Material not passing through an 8 mesh sieve	0%

For example, using the above criteria, two limestones with different sieve fractions would be rated as follows using the Ohio method:

SIEVE FRACTIONS	LIMESTONE A	LIMESTONE B
Passing through a 60 mesh sieve	78.8%	90.0%
Passing through a 20, but not a 60 mesh sieve	10.0%	6.0%
Passing through an 8, but not a 20 mesh sieve	2.4%	4.0%
Not passing through an 8 mesh sieve	7.8%	0%

$$\begin{aligned} A &= (78.8 \times 1.00) + (10 \times 0.60) + (2.4 \times 0.20) \\ &= 78.8 + 6 + 0.48 \\ &= 85.28\% \end{aligned}$$

$$\begin{aligned} B &= (90.0 \times 1.00) + (6 \times 0.60) + (4.0 \times 0.20) \\ &= 90 + 3.6 + 0.8 \\ &= 94.46\% \end{aligned}$$

This rating suggests that limestone A would be about 10% less efficient than limestone B. This calculation implies that roughly 10% more of limestone A would be required to achieve the same change in soil pH as would be obtained with a given quantity of limestone B.

2. Neutralizing Capacity

Another factor which influences the efficiency of a limestone is its neutralizing capacity. This is determined by reacting limestone with strong acids, either hydrochloric or sulphuric acid. The limestone's neutralizing capacity is expressed as a percentage value of pure calcium carbonate, which has a neutralizing value of 100%. Commercial limestones may have neutralizing capacities greater or lesser than pure CaCO_3 . Dolomitic limestone (a mixture of magnesium and calcium carbonates) has a theoretic neutralizing value of 108%. Generally, limestones have neutralizing values below 100%. Impurities such as clays in limestone reduce their relative neutralizing capacities.

To determine the agricultural value (A.V.) of limestones, the particle size efficiency rating (E.R.) has to be adjusted by the neutralizing value (N.V.) (synonymous with neutralizing capacity), plus an adjustment for limestone moisture content (M.C.). For example, a limestone having an efficiency rating (E.R.) of 85%, a neutralizing value (N.V.) of 95%, and a moisture content of (M.C.) 13%, has an agricultural value of:

$$\begin{aligned} \text{AV} &= 85\% (\text{E.R.}) \times 0.95 (\text{N.V.}) \times [1.00 - 0.13 \text{ M.C.}] \\ \text{AV} &= 70.25\% \end{aligned}$$

3. Solubility and Magnesium Content

Limestone solubility is not frequently evaluated by routine tests, but also influences the neutralizing rate of soil acidity. The crystalline structure and chemical composition of limestones vary due to their geological formation. Dolomitic limestones, having a combination of magnesium and calcium carbonates, are less soluble than either calcitic limestones (CaCO_3) or magnesium carbonate. Dolomite is, however, useful on acidic soils low in magnesium.

The Soil, Feed and Tissue Lab will perform a limestone analysis at a cost of \$20.00 per sample. This includes a determination of neutralizing value, calcium and magnesium content, particle size classification, and agricultural value rating and an interpretation of results.

4. Other Liming Materials

At low liming rates, around 2 tonnes/ha (1 ton/acre), calcium hydroxide (slaked lime) can be substituted for limestone by multiplying the recommended rates by 0.84. The main advantage in using calcium hydroxide [$\text{Ca}(\text{OH})_2$] is its quick neutralizing capacity, which is due to being very finely pulverized. The disadvantages are that it costs substantially more, may cause overliming problems, and is unpleasant to handle in large quantities due to its caustic nature.

FOR FURTHER INFORMATION, CONTACT:

Geoff Huges-Games, Prov. Soil Specialist (Written by Dr. W. van Lierop, Kelowna)
Phone: (604) 556-3102
Email: Geoff.HughesGames@gems7.gov.bc.ca

RESOURCE MANAGEMENT BRANCH

Ministry of Agriculture and Food
1767 Angus Campbell Rd.
Abbotsford, BC CANADA V3G 2M3